

FEDERAL REPUBLIC OF GERMANY



Priority Certificate for the filing of a Patent Application

File Reference: 103 50 420.6

Filing date: 28 October 2003


Applicant/Proprietor: BASF Aktiengesellschaft/ 67056 LudwigshafenDE

Title: Use of copolymers containing alkylene oxide units as film-inhibiting additives in the clear-rinse cycle of a dishwasher

IPC: C 11 D 3/37

The attached documents are a correct and accurate reproduction of the original submission for this application.

Munich, 12 August 2004
German Patent and Trademark Office
The President
pp



[signature]
Wehner


Claims

1. The use of copolymers containing alkylene oxide units and comprising, in randomly or blockwise copolymerized form,

- (a) 50 to 93 mol% of acrylic acid and/or a water-soluble salt of acrylic acid,
(b) 5 to 30 mol% of methacrylic acid and/or a water-soluble salt of methacrylic acid

and

- (c) 2 to 20 mol% of at least one nonionic monomer of the formula I



in which the variables have the following meanings:

- R^1 is hydrogen or methyl;
 R^2 is a chemical bond or unbranched or branched $\text{C}_1\text{-C}_6$ -alkylene;
 R^3 is identical or different unbranched or branched $\text{C}_2\text{-C}_4$ -alkylene radicals;
 R^4 is unbranched or branched $\text{C}_1\text{-C}_6$ -alkyl;
 n is 3 to 50,

as film-inhibiting additives in the clear-rinse cycle of a dishwasher.

2. The use according to claim 1, wherein the copolymers comprise 65 to 85 mol% of component (a), 10 to 25 mol% of component (b) and 5 to 15 mol% of component (c) in copolymerized form.
3. The use according to claim 1 or 2, wherein the copolymers comprise 65 to 75 mol% of component (a), 15 to 25 mol% of component (b) and 5 to 10 mol% of component (c) in copolymerized form.
4. The use according to claims 1 to 3, wherein the copolymers comprise, as component (c), a nonionic monomer of the formula I, in which R^1 is methyl, R^2 is a chemical bond, R^3 is $\text{C}_2\text{-C}_3$ -alkylene, R^4 is $\text{C}_1\text{-C}_2$ -alkyl and n is 5 to 40, in copolymerized form.

5. The use according to claims 1 to 4, wherein the copolymers comprise, as component (c), a nonionic monomer of the formula I, in which R^1 is methyl, R^2 is a chemical bond, R^3 is ethylene, R^4 is methyl and n is 10 to 30, in copolymerized form.
6. The use according to claims 1 to 5, wherein the copolymers contain $-SO_3^- Na^+$ and/or $-SO_4^- Na^+$ as end groups.
7. The use according to claims 1 to 6, wherein the copolymers are used in rinse aids for dishwashers.
8. The use according to claims 1 to 6, wherein the copolymers are used in a form formulated into the rinse aid core of a detergent tablet for dishwashers.
9. A rinse aid for dishwashers which comprises copolymers according to claims 1 to 6 as film-inhibiting additive.
10. A detergent tablet for dishwashers which comprises copolymers according to claims 1 to 6 as film-inhibiting additive formulated into the rinse aid core.

1

Use of copolymers containing alkylene oxide units as film-inhibiting additives in the clear-rinse cycle of a dishwasher

Description

5

The present invention relates to the use of copolymers containing alkylene oxide units and comprising, in randomly or blockwise copolymerized form,

10


(a) 50 to 93 mol% of acrylic acid and/or a water-soluble salt of acrylic acid,

(b) 5 to 30 mol% of methacrylic acid and/or a water-soluble salt of methacrylic acid

and

15

(c) 2 to 20 mol% of at least one nonionic monomer of the formula I



in which the variables have the following meanings:

20

R^1 is hydrogen or methyl;

R^2 is a chemical bond or unbranched or branched C_1 - C_6 -alkylene;

R^3 is identical or different unbranched or branched C_2 - C_4 -alkylene radicals;

R^4 is unbranched or branched C_1 - C_6 -alkyl;

25

n is 3 to 50,

as film-inhibiting additives in the clear-rinse cycle of a dishwasher.

30 In addition, the invention relates to rinse aids for dishwashers which comprise these copolymers as film-inhibiting additive, and also to detergent tablets for dishwashers which comprise the copolymers formulated into the rinse aid core as film-inhibiting additive.

35 In the case of machine dishwashing, the ware should be obtained in a residue-free cleaned state with a flawlessly shiny surface. The ware should not only be completely cleaned of food residues, but should also have no whitish marks which arise due to the presence of limescale or other inorganic and organic salts as water drops dry up.

2

For this reason, rinse aids have been used for a relatively long time. Here, the rinse aid is automatically released from a dosing chamber in the inside of the dishwasher in the clear-rinse cycle following completion of the wash program, which usually consists of a prewash cycle and a main wash cycle interrupted by interim rinse cycles, and ensures that the water during the clear-rinse cycle and drying cycle runs off from the ware in a manner which is flat and as complete as possible, and the surfaces of the ware are residue-free and flawlessly shiny at the end of the wash program.


In the case of the so-called "2in1" detergents on the market, clear-rinse surfactants have already been integrated into the detergent formulation, meaning that it is possible to dispense with the additional dosing of a rinse aid.

Modern machine "3in1" detergents combine the three functions of cleaning, clear rinsing and water softening in a single detergent formulation, meaning that for the consumer the topping-up of salt for water hardnesses from 1 to 3 becomes superfluous. To bind the hardness-forming calcium and magnesium ions, sodium tripolyphosphate is usually added to these detergents. This, however, again results in calcium phosphate and magnesium phosphate films on the ware.

The object of the invention was to provide polymeric additives which are characterized by their film-inhibiting effect when used in the clear-rinse cycle of a dishwasher.

Accordingly, the use of copolymers containing alkylene oxide units which comprise, in randomly or blockwise copolymerized form,

- (a) 50 to 93 mol% of acrylic acid and/or a water-soluble salt of acrylic acid,
- (b) 5 to 30 mol% of methacrylic acid and/or a water-soluble salt of methacrylic acid and



in which the variables have the following meanings:

- R¹ is hydrogen or methyl;
- R² is a chemical bond or unbranched or branched C₁-C₆-alkylene;
- R³ is identical or different unbranched or branched C₂-C₄-alkylene radicals;
- R⁴ is unbranched or branched C₁-C₆-alkyl;
- n is 3 to 50,

as film-inhibiting additives in the clear-rinse cycle of a dishwasher has been found.

In addition, rinse aids for dishwashers which comprise these copolymers as film-inhibiting additive have been found.

In addition, detergent tablets for dishwashers have been found which comprise these copolymers as film-inhibiting additive formulated into the rinse aid core.


The copolymers to be used according to the invention are described in the earlier German patent application as additive for detergents and cleaners.

The copolymers containing alkylene oxide units to be used according to the invention contain, as copolymerized components (a) and (b), acrylic acid and methacrylic acid and/or water-soluble salts of these acids, in particular the alkali metal salts, such as potassium salts and especially sodium salts, and ammonium salts.

The amount of acrylic acid (a) in the copolymers to be used according to the invention is 50 to 93 mol%, preferably 65 to 85 mol% and particularly preferably 65 to 75 mol%.

Methacrylic acid (b) is present in the copolymers to be used according to the invention in an amount of from 5 to 30 mol%, preferably in an amount of from 10 to 25 mol% and especially in an amount of from 15 to 25 mol%.

The copolymers contain, as component (c), nonionic monomers of the formula I



in which the variables have the following meanings:

- R^1 is hydrogen or preferably methyl;
 R^2 is unbranched or branched C_1 - C_6 -alkylene or preferably a chemical bond;
 R^3 is identical or different unbranched or branched C_2 - C_4 -alkylene radicals, especially C_2 - C_3 -alkylene radicals, in particular ethylene;
 R^4 is unbranched or branched C_1 - C_6 -alkyl, preferably C_1 - C_2 -alkyl;
 n is 3 to 50, preferably 5 to 40, particularly preferably 10 to 30.

Particularly suitable examples of the monomers II which may be mentioned are: methoxypolyethylene glycol (meth)acrylate, methoxypolypropylene glycol (meth)acrylate,

4

methoxypolybutylene glycol (meth)acrylate, methoxypoly(propyleneoxide-co-ethyleneoxide) (meth)acrylate, ethoxypolyethylene glycol (meth)acrylate, ethoxypolypropylene glycol (meth)acrylate, ethoxypolybutylene glycol (meth)acrylate and ethoxypoly(propylene oxide-co-ethylene oxide) (meth)acrylate, where methoxypolyethylene glycol (meth)acrylate and methoxypolypropylene glycol(meth) acrylate are preferred and methoxypolyethylene glycol methacrylate is particularly preferred.

The polyalkylene glycols here contain 3 to 50, in particular 5 to 40 and especially 10 to 30 alkylene oxide units.

The amount of nonionic monomers (c) in the copolymers to be used according to the invention is 2 to 20 mol%, preferably 5 to 15 mol% and especially 5 to 10 mol%.

The copolymers to be used according to the invention generally have an average molecular weight M_w of from 3 000 to 50 000, preferably from 10 000 to 30 000 and particularly preferably from 15 000 to 25 000.

The K value of the copolymers is usually 15 to 40, in particular 20 to 35, especially 27 to 30 (measured in 1% strength by weight aqueous solution at 25°C, in accordance with H. Fikentscher, Cellulose-Chemie, Vol. 13, pp. 58-64 and 71-74 (1932)).

The copolymers to be used according to the invention can be prepared by free-radical polymerization of the monomers. In this connection, all known free-radical polymerization processes can be used. Besides bulk polymerization, the processes of solution polymerization and of emulsion polymerization are to be mentioned in particular, with solution polymerization being preferred.

The polymerization is preferably carried out in water as solvent. It can, however, also be carried out in alcoholic solvents, in particular C₁-C₄-alcohols, such as methanol, ethanol and isopropanol, or mixtures of these solvents with water.

Suitable polymerization initiators are compounds which either decompose thermally or photochemically (photoinitiators) to form free radicals.

Among the thermally activatable polymerization initiators, preference is given to initiators with a decomposition temperature in the range from 20 to 180°C, in particular from 50 to 90°C. Examples of suitable thermal initiators are inorganic peroxo compounds, such as peroxodisulfates (ammonium and preferably sodium peroxodisulfate), peroxosulfates, percarbonates and hydrogen peroxide; organic peroxo compounds, such as diacetyl peroxide, di-tert-butyl peroxide, diamyl peroxide, dioctanoyl peroxide, didecanoyl peroxide, dilauroyl peroxide, dibenzoyl peroxide, bis(o-tolyl) peroxide, succinyl

5

peroxide, tert-butyl peracetate, tert-butyl permaleate, tert-butyl perisobutyrate, tert-butyl perpivalate, tert-butyl peroctoate, tert-butyl perneodecanoate, tert-butyl perbenzoate, tert-butyl peroxide, tert-butyl hydroperoxide, cumene hydroperoxide, tert-butyl peroxy-2-ethylhexanoate and diisopropyl peroxydicarbamate; azo compounds, such as

5 2,2'-azobisisobutyronitrile, 2,2'-azobis(2-methylbutyronitril) and azobis(2-amidopropane) dihydrochloride.

These initiators can be used in combination with reducing compounds as starter/regulator systems. Examples of such reducing compounds which may be men-

10 tioned are phosphorus-containing compounds, such as phosphorus acid, hypophosphites and phosphinates, sulfur-containing compounds, such as sodium hydrogen sulfite, sodium sulfite and sodium formaldehyde sulfoxilate, and hydrazine.

Examples of suitable photoinitiators are benzophenone, acetophenone, benzoin ether,

15 benzyl dialkyl ketones and derivatives thereof.

Preferably, thermal initiators are used, preference being given to inorganic peroxo compounds, in particular sodium peroxodisulfate (sodium persulfate). The peroxo compounds are advantageously used in combination with sulfur-containing reducing

20 agents, in particular sodium hydrogensulfite, as redox initiator system. The use of this starter/regulator system produces copolymers which contain $\text{-SO}_3^- \text{Na}^+$ and/or $\text{-SO}_4^- \text{Na}^+$ as end groups and are characterized by particular film-inhibiting effect.

Alternatively, it is also possible to use phosphorus-containing starter/regulator systems, e.g. hypophosphites/phosphinates.

25

The amounts of photoinitiator and/or starter/regulator system should be matched to the substances used in each case. If, for example, the preferred system of peroxodisulfate/hydrogensulfite is used, then usually 2 to 6% by weight, preferably 3 to 5% by

30 weight of peroxodisulfate and usually 5 to 30% by weight, preferably 5 to 10% by weight, of hydrogensulfite, in each case based on the monomers (a), (b) and (c), are used.

If desired, it is also possible to use polymerization regulators. Suitable compounds are those known to the person skilled in the art, e.g. sulfur compounds, such as mercaptoethanol, 2-ethylhexyl thioglycolate, thioglycolic acid and dodecyl mercaptan. If polymerization regulators are used, their use amount is usually 0.1 to 15% by weight, preferably 0.1 to 5% by weight and particularly preferably 0.1 to 2.5% by weight, based on the monomers (a), (b) and (c).

35

The polymerization temperature is usually 30 to 200°C, preferably 50 to 150°C and particularly preferably 80 to 120°C.

5 The polymerization can be carried out under atmospheric pressure, although it is preferably carried out in a closed system under the autogenous pressure which develops.

10 In the preparation of the copolymers to be used according to the invention, the monomers (a), (b) and (c) can be used as they are, although it is also possible to use reaction mixtures which are produced in the preparation of the monomers (c). Thus, for example, instead of methoxypolyethylene glycol methacrylate, it is possible to use the monomer mixture produced during the esterification of polyethylene glycol monomethyl ether with an excess of methacrylic acid. Advantageously, the esterification can also be carried out in situ in the polymerization mixture by mixing together in parallel (1) acrylic acid, (2) a mixture of methacrylic acid and polyethylene glycol monomethyl ether and (3) free-radical initiator. Where appropriate, a catalyst necessary for the esterification, such as methanesulfonic acid or p-toluene sulfonic acid, can be additionally used.

20 The copolymers to be used according to the invention can also be prepared by a polymer-analogous reaction, e.g. by reacting an acrylic acid/methacrylic acid copolymer with polyalkylene glycol monoalkyl ether. However, preference is given to the free-radical copolymerization of the monomers.

25 If desired for the application, the aqueous solutions produced during the preparation of the copolymers containing carboxylic acid groups to be used according to the invention can be neutralized or partially neutralized, i.e. to a pH in the range 4 - 8, preferably 4.5 - 7.5, by adding base, in particular sodium hydroxide solution.

30 The copolymers used according to the invention are characterized by their excellent film-inhibiting effect when used in the clear-rinse cycle of a dishwasher.

35 In this connection, they have an inhibiting effect both for inorganic and organic films. In particular, mention may be made of films which are caused by the constituents of the detergent formulation entrained into the clear-rinse cycle by the "carry-over effect", such as films of calcium phosphate and magnesium phosphate, calcium silicate and magnesium silicate and calcium phosphonate and magnesium phosphonate, and films which originate from the soiling constituents of the wash liquor, such as grease, protein and starch films. The copolymers to be used according to the invention improve the cleaning result with lasting effect as a result of their film-inhibiting effect. In addition, even at low concentrations, they favor the run-off of water from the ware, meaning that the amount of clear-rinse surfactants in the dishwashing detergents can be reduced.

Accordingly, particularly clear glassware and very shiny metal cutlery items are obtained, particularly also when the dishwasher is operated without regenerating salt to soften the water.

- 5 The copolymers used according to the invention can be used directly in the form of the aqueous solutions produced during the preparation, or else in dried form obtained, for example, by spray drying, fluidized spray drying, drum drying or freeze-drying.

10 The copolymers according to the invention can advantageously be used in particular as follows:

- dissolved in a rinse aid formulation which is automatically metered in the dishwasher at the start of the clear-rinse cycle.
- 15 - formulated into the clear-rinse core of a dishwasher tablet from which they are released in a targeted manner in the clear-rinse cycle.
- in the form of a solid obtained by one of the methods described above, which is additionally provided with a coating which is soluble under the clear-rinse conditions (temperature, pH, residual concentration of detergent components in the
20 clear-rinse cycle), or is incorporated into a matrix which is soluble under these conditions, and is introduced into the machine together with the detergent, but is only released in the clear-rinse cycle.
- 25 A suitable coating material for this purpose is, for example, polyvinyl alcohol prepared by incomplete hydrolysis of polyvinyl acetate (degree of hydrolysis of usually 88 to 98%, preferably 89 to 95%, particularly preferably 91 to 92%).
- 30 Suitable matrix materials are, for example, gelatin, polyvinyl alcohol, polyvinylpyrrolidone, polyethylene oxide, cellulose and derivatives thereof, starch and derivatives thereof and mixtures of these materials.

Use of copolymers containing alkylene oxide units as film-inhibiting additives in the clear-rinse cycle of a dishwasher

Abstract

5

Use of copolymers containing alkylene oxide units and comprising, in randomly or blockwise copolymerized form,

10


(a) 50 to 93 mol% of acrylic acid and/or a water-soluble salt of acrylic acid,

(b) 5 to 30 mol% of methacrylic acid and/or a water-soluble salt of methacrylic acid

and

15

(c) 2 to 20 mol% of at least one nonionic monomer of the formula I



in which the variables have the following meanings:

20

R^1 is hydrogen or methyl;

R^2 is a chemical bond or unbranched or branched C_1 - C_6 -alkylene;

R^3 is identical or different unbranched or branched C_2 - C_4 -alkylene radicals;

R^4 is unbranched or branched C_1 - C_6 -alkyl;

25

n is 3 to 50,

as film-inhibiting additives in the clear-rinse cycle of a dishwasher.